

Sea-Bird Electronics, Inc. 1808 136th Place NE Bellevue, WA 98005 USA

APPLICATION NOTE NO. 66

AUGUST 2001

Routine Maintenance for the SBE 32 Carousel Water Sampler

This Application Note reviews corrosion precautions and routine maintenance for the SBE 32 Carousel Water Sampler. The reliability of the Carousel is sustained by establishing proper handling practices.

Corrosion Precautions/Cleaning

Rinse the entire Carousel with fresh water after each cast.

The Carousel's trigger mechanism is made of titanium. The titanium is coated with Tiodizing; this product is similar to anodizing aluminum. **The Tiodized surface is water lubricating and should never be oiled with petroleum or silicon-based products**. Rinse the trigger mechanism with fresh water after each cast and clean it periodically with warm, soapy water. If the trigger mechanism sticks after this cleaning, remove the latch assembly and immerse the whole assembly in warm, soapy water. See *Removing / Replacing Latch Assembly* below.

Large zinc anodes provide corrosion protection:

- SBE 32C and 32SC two each in lower adapter plate, lower guard ring, upper adapter plate, upper guard ring; one on pylon/hub assembly
- SBE 32 (standard)
 - 12-bottle size three each on lower guard ring and upper guard ring; two on lower adapter plate; one on pylon/hub assembly
 - 24-bottle size three each in lower adapter plate, lower guard ring, upper adapter plate, upper guard ring; one on pylon/hub assembly
- CTD extension stand (if used) two
- Check the anodes occasionally to verify that they are securely fastened and have not eroded.

All screws that are exposed to seawater have been generously lubricated with an anti-seize compound, Never-Seez Blue Moly, manufactured by Bostik (available through marine hardware stores). When disassembling/reassembling the Carousel, re-lubricate these screws with Blue Moly or equivalent. This compound is electrically conductive, so be careful not to get it on circuit boards.

Note: Blue Moly is molybdenum disulfide and pure nickel flake in pressure-resistant premium grade grease, formulated *without* graphite, lead, or copper. See Bostik's website (http://www.bostik.com/pdf/distribution/N2BlueMoly.pdf) for the most up-to-date specification; a copy of Bostik's current product data sheet is included at the end of this Application Note for your convenience.


Removing/Replacing Latch Assembly


Removing Latch Assembly


- 1. Remove the three socket hex head screws, lock washers, and flat washers from the top of the latch assembly. Lift the latch assembly off the pylon.
- 2. Remove individual triggers if desired:
 - A. Mark the location of trigger 1 (from the retainer disk) on the trigger mount disk to aid in reassembly.
 - B. Remove the Phillips-head screws (eight for 32C and 32SC, six for full-size 32). Lift the retainer disk from the top of the latch assembly.
 - C. Pull the desired trigger(s) horizontally from the trigger mount disk. Mark the trigger(s) to aid in reassembly.

Replacing Latch Assembly

- 1. Replace the triggers on the trigger mount disk.
- 2. Place the retainer disk on the triggers, aligning the mark you made for trigger 1 on the trigger mount disk with trigger 1 on the retainer disk. Verify that the triggers are properly seated in the grooves and that the disk is flat. Reinstall the Phillips-head screws loosely. Tighten the screws, working in a diagonal pattern to ensure the disk remains properly seated.
- 3. Line up the latch assembly alignment hole with the pylon alignment pin. Seat the latch assembly on the pylon. Reinstall the three socket hex head screws, lock washers, and flat washers.







Retainer disk and Phillipshead screws

Alignment hole for position 1 for replacement on pylon



Removing Center Pylon

- 1. Remove the lifting bail.
 - A. Remove the hardware from underneath the lower guard ring.
 - B. Begin to pull the lifting bail up, until it is above the lower guard ring/adapter plate/hub assembly connection.
 - C. Remove the hardware from the legs of the lifting bail.
 - D. Pull the lifting bail out of the upper guard ring.

NOTE:

There are plastic insulators on the underside of the following connections:

- Lower guard ring/adapter plate/hub assembly for lifting bail
- Upper adapter plate for pylon

Verify that the insulators have not fallen out before reinstalling the pylon and lifting bail.

2. Remove the 6 socket hex head cap screws and washers from the underside of the upper adapter plate. Pull the trigger assembly with the pylon up and out of the Carousel frame.

Never-Seez Blue Moly Data Sheet



Blue Moly

Product Description

Never-Seez Blue Moly is a superior lubricating and anti-seize compound formulated to provide maximum parts protection in a wide range of applications. The exclusive combination of molybdenum disulfide and pure nickel flake suspended in a premium-grade grease provides both excellent lubricity and extreme pressure resistance. Blue Moly is especially recommended for those applications in which graphite, lead, and copper are prohibited or undesirable. The addition of special corrosion inhibitors allows Blue Moly to be used in harsh environments.

Product Benefits

- Excellent protection against extreme pressure.
- Excellent temperature protection, up to 1500°F.
- Unique blue color allows for easy visual inspection.
- Contains no graphite, lead or copper, therefore Blue Moly can be used in applications where these are undesirable or prohibited.

Product Applications

Metal fittings

- Aircraft components
- Valves
- Stainless steel fasteners and slow moving parts
- · Automotive engine bolts and body fasteners
- Stainless steel flange and pump bolts
- · Chemical processing machinery
- Gasket dressing
- Assembly of dissimilar metals

Limitations

- Never-Seez Blue Moly is not recommended for high speed bearings. Never-Seez Red Bearing Lubricant is suggested for these applications.
- For temperature resistance to 2400°F, use Never-Seez Pure Nickel Special.

Other Anti-Selze Lubricants from Bostik

- Regular Grade
- Nuclear Grade, Nickel Special
- Pure Nickel Special
- High Temp Stainless
- · High Temp Stainless, Nuclear Certified
- Marine Grade
- · Black Moly Lubricant
- Red Bearing Lubricant
- White Food Grade with PTFE
- High Temperature Bearing Lubricant
- Pipe Compound with Teflon®

® Teflon is a Registered Trademark of Dupont.



Technical Specifications

reclinical opecifications			
Color	Blue		
Temperature Range, °F	-150 to 1500		
Solvent Resistance	Excellent in fresh o	Excellent in fresh or salt water	
Particle Size, mil	2 maximum		
Specific Gravity	1.14 to 1.20		
		ASTM Test Method	
NLGI Grade	1/2	D-217	
Worked Penetration (60 Strokes)	300-350	D-217	
Flash Point, °F	383	D-92	
Dropping Point, °F	360	D-566	
Copper Corrosion Test (212°F, 24 hours)	No Corrosion	D-130-83	
Coefficient of Friction, k factor	.150		
Coefficient of Friction (4 ball), 167°F	.0824	D-2266	
Extreme Pressure, psi	N/A		

Ingredients: Contains a special, high-quality bearing grease with nickel flake, molybdenum sulfide and aluminum flake.

Shelf Life: NEVER-SEEZ Blue Moly does not deteriorate with age when stored unopened at temperatures below 120°F. Quality and performance are guaranteed for five years from the date of manufacture on unopened containers.

Use in accordance with Material Safety Data Sheet.

Ordering Informatio	on	
BLUE MOLY		
STOCK NUMBER	DESCRIPTION	SIZE
NB-160	Flat Top	1 lb.
NB-8	Flat Top	8 lb.
NBBT-8	Brush Top	8 oz.
NPBT-16	Brush Top	1 lb.
NB-42B	Pail	42 lb.

IMPORTANT NOTICE:

Bostik Findley, Inc.

211 Boston Street Middleton, MA 1949-2128 U.S.A. Technical Service: 888-603-8558 FAX: 978-750-7293 http://www.bostikfindley-us.com

All statements, technical information and recommendations set forth herein are based on tests which Bostik Findley, Inc. All statements, technical information and recommendations set forth herein are based on tests which Bostik Findley, Inc. believes to be reliable. However, Bostik Findley does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on Bostik Findley's order acknowledgment. Bostik Findley, Inc. warrants that the product conforms with Bostik Findley's written specifications, and is free from defects. BOSTIK FINDLEY, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH THIS WARRANTY SHALL BE FOR THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK FINDLEY BE LIABLE FOR DIRECT, CONSEQUENTIAL ECONOMIC OR OTHER DAMAGES. N2-06/01-5M

N2-06/01-5M